



brentwood plastics, inc.

3122 Sutton Boulevard
Maplewood, MO 63143

www.brentwoodplastics.com

Phone: 314.968.1135

Fax: 314.968.4276

622

622 is a proprietary blend of metallocenes and linear low designed to seal rapidly through contaminants. Used mostly as a sealant layer in laminations. FDA and Kosher approved. Unless otherwise requested, COF is 0.20 maximum.

<u>Properties</u>	<u>test method</u>	<u>typical value*</u>	<u>unit</u>
Haze	ASTM D 1003	8.9	%
Gloss 45 °	ASTM D 2457	68	-
1% secant modulus	ASTM D 882	25,000	psi
MD		26,200	
TD			
Dart Impact F50	ASTM D1709A	224	gm.
Elmendorf tear	ASTM D 1922	304	gm.
MD		490	
TD			
Tensile Break Strength	ASTM D 882	3,400	psi
MD		3,800	
TD			
Tensile Elongation @ break			
MD		490	%
TD		650	%
Tensile Yield			
MD		1,550	psi
TD		1,400	psi
Elongation @ yield			
MD		18.4	%
TD		17.6	%
Seal initiation temperature	BPI	255	° F

* data obtained on 2.0 mil film is typical and not to be construed as specification limits. Establishing suitability for any end use is the end user's responsibility. No warranties are expressed or implied.