

GEL SPECIFICATION

1.0 **Scope:** Applies to all products that require defect sizing (i.e. gels, carbon specs, etc.) when tolerances are not specified by the Customer.

2.0 **Reference** CHPWI-0098 for test procedure.

3.0 **Specification:**

<u>Size (Sq. mm)</u>	<u>Maximum Allowed</u>
.15 or less	Acceptable
.15 to less than .60	10 / Sq. Ft.
.60 to less than 1.50	2 / Sq. Ft.
Greater than 1.50	None

Carbon

<u>Size (Sq. mm)</u>	<u>Maximum Allowed</u>
.10 or less	Acceptable
.10 to less than .40	2 / Sq. Ft.
Greater than .40	None

