



brentwood plastics, inc.

3122 Sutton Boulevard
Maplewood, MO 63143

www.brentwoodplastics.com

Phone: 314.968.1135
Fax: 314.968.4276

PCO29

PCO29 is a high clarity film designed for retail bag packaging. Offers unique combination of low seal initiation temperature and stiffness for maximum cycle speed on automatic wicketers. Strong seals make it a natural for whole produce bags.

Typical Properties *

| <u>Property</u> | <u>Test Method</u> | <u>Typical Value</u> | <u>Unit</u> |
|--|--------------------|------------------------|-------------|
| Haze | ASTM D 1003 | 6 | % |
| Gloss 45° | ASTM D 2457 | 74 | - |
| Secant Modulus | ASTM D 882 | 42,000 MD 41,500 TD | psi |
| Dart Impact F 50 | ASTM 1709 A | 210 | gm |
| Tensile Elongation | ASTM D 882 | | % |
| MD Yield | | 19 | |
| Break | | 355 | |
| TD Yield | | 16 | |
| Break | | 720 | |
| Coefficient of Friction untreated to untreated | ASTM D 1894 | 0.18 | |

* good faith estimates based on nominal 1.5 mil film @ 2.05 BUR
Not to be construed as specification limits
It is the users responsibility to determine suitability for any application, no warranties are expressed or implied.